

# NASA TECH BRIEF



NASA Tech Briefs are issued to summarize specific innovations derived from the U. S. space program and to encourage their commercial application. Copies are available to the public from the Clearinghouse for Federal Scientific and Technical Information, Springfield, Virginia 22151.

## Protective Coating Withstands High Temperatures in Oxidizing Atmosphere

### The problem:

To provide a protective coating that will withstand high temperatures in an oxygen-rich atmosphere such as the flames of a liquid oxygen-kerosene rocket engine. Used on a thermocouple, it must be thin enough so that response time is not degraded but must protect the base material for a sufficient time to permit proper temperature measurement. It is also desirable to be able to use the coated thermocouple through more than one heating/cooling cycle without cracking, chipping, or peeling.

### The solution:

A plasma arc sprayed mixture of hafnium oxide and zirconium diboride.

### How it's done:

A mixture of hafnium oxide and zirconium diboride in a 1:1 ratio based on the atomic weight of the metal is prepared with a particle size distribution of between approximately -125 and +325 mesh and an average particle size of about 200 mesh. The powdered mixture is dispersed in an inert gas that passes through an electrical discharge arc at a typical temperature of 3000° to 5000°K. The resultant plasma jet is a hot, fluid, gaseous stream and is directed toward the substrate to be coated, this being

surrounded by a cooling atmosphere of an inert gas such as argon. The plasma jet stream condenses on the cooled substrate surface to provide the desired protective coating.

### Notes:

1. A coating of the order of 0.002 to 0.050 inch on a homogeneous tungsten thermocouple surface gave good protection, did not flake or crack on subsequent cooling and reheating, and did not degrade the thermocouple response time.
2. This coating withstood a temperature of 4700°F for 5 minutes with no apparent damage to the substrate. Exposure to 3700°F for 30 minutes gave the same result.

### Patent status:

Title to this invention has been waived under the provisions of the National Aeronautics and Space Act (42 U.S.C. 2457 (f)), to Fenwal Incorporated, Ashland, Massachusetts.

Source: Clarence Howard Mellor  
of Fenwal Incorporated  
under contract to  
Marshall Space Flight Center  
(M-FS-529)

Category 03